DESCOR®
Opaque

Fields of application

.01 .02 .03 .04 .07

Specifications

REF. 599159 151

100 % polyester
knit fabrics
PVC-free, recyclable

ca. 160/ 252/ 320/ 505 cm
ca. 63/ 99/ 126/ 199 inch
other widths available on request

B-s1, d0 DIN EN 13501-1

ca. 210 g/m²
ca. 6.2 oz/yd²

ca. 0.37 mm
ca. 370 µm

rolls
50/ 100 m
55/ 109 yd

length: 448.7 N
cross: 683.6 N
DIN EN ISO 13934-1

length: 31.4 %
cross: 53.3 %
DIN EN ISO 13934-1

blank: 7
DIN EN ISO 105-B02

blank: 88.76
DIN 5033-1

length: 0.9 %
cross: 0.7 %
DIN EN 14704-1

cold, ultrasonic cut

Specs luminance factor
blank: 0,93
DIN 19045-4

Printing methods

print	UV	Latex	Dyesub	UVgel
Inside	•		•	•
Outside				

Article shrinkage
(33 sec hold up time)

	shrinkage in cross direction	shrinkage in longitudinal direction	recommended fixing temperature
180°C	0,5 %	1,2 %	185
190°C	/ %	/ %	
200°C	/ %	/ %	
210°C	/ %	/ %	

Certifications

OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100 09.0.67573 HOHENSTEIN HTTI Tested for harmful substances. www.oeko-tex.com/standard100

PONGS GROUP GMBH & CO. KG
Bahnhofstraße 21
07919 Pausa-Mühltroff
Germany
Phone +49 36645 350-0
salestt@pongs.com
www.pongs.com

Find the latest version by scanning the QR code.
We reserve the right for technical modifications.
The above mentioned details are non-binding.
A tolerance of ± 5% is valid. Effective: 2022/02

DESCOR®
Opaque

Fields of application

.01 .02 .03 .04 .07

Ref.-Nr.: 599150 150 | Preview print sample

PONGS GROUP GMBH & CO. KG
Bahnhofstraße 21
07919 Pausa-Mühltroff
Germany

Phone +49 36645 350-0
salestt@pongs.de
www.pongs.com

We reserve the right for technical modifications.
The above mentioned details are non-binding.
A tolerance of ± 5% is valid. Effective: 2022/02